



# Ti-Pure™

## R-706 Titanium Dioxide

## Product Information

### Product Description

Ti-Pure™ R-706 is a universal rutile titanium dioxide pigment, manufactured by the chloride process, that is designed to deliver both high gloss and excellent durability in coatings. This outstanding combination of end-use performance properties makes it a versatile pigment in solvent and waterborne systems for architectural, industrial, and automotive applications. Ti-Pure™ R-706 has the following general properties.

**Table 1.**

Analysis and Physical Properties of Ti-Pure™ R-706

Property	R-706
TiO <sub>2</sub> , wt%, min.	93
Alumina, wt%	2.5
Amorphous Silica, wt%	3.0
Specific Gravity	4.0
Bulking Value, L/kg (gal/lb)	0.25 (0.03)
Organic Treatment	Yes
Color CIE L*	99.4
Median Particle Size, μm	0.36
Oil Absorption	13.9
pH	8.2
Resistance at 30 °C (86 °F) (1,000 ohm)	10
Carbon Black Undertone	13.8

Note: All values are typical unless otherwise specified.

### Key Features

- High gloss
- Super durability
- Excellent dispersibility
- Easy wet-in
- Good hiding
- Blue undertone

### High Gloss

Careful control of the TiO<sub>2</sub> particle size during manufacture of R-706 results in exceptional gloss performance. R-706 has a tight particle size distribution, resulting in less oversized particles that detract from gloss.

### Super Durability

Unique encapsulation of the TiO<sub>2</sub> particle by a continuous coating of silica (SiO<sub>2</sub>) is responsible for the excellent durability of R-706. Florida exposure data for R-706 shows excellent gloss retention and chalk resistance.

### Excellent Dispersibility

The alumina (Al<sub>2</sub>O<sub>3</sub>) surface treatment reduces the contact between TiO<sub>2</sub> particles, resulting in excellent dispersion of R-706 in solventborne systems. To further enhance dispersion, we apply an organic treatment during manufacture.

### Easy Wet-in

Novel precipitation of the silica and alumina surface treatments result in the low oil absorption properties of R-706 that are responsible for its excellent wet-in. Less power required for R-706 wet-in could result in productivity gains and capacity increases.

### Good Hiding

The low surface treatment levels, 3% amorphous silica and 2.5% alumina, result in a high TiO<sub>2</sub> content for R-706, contributing to good hiding. The mean particle size of R-706 approaches the optimum particle size for scattering efficiency.

### Blue Undertone

Small particle size TiO<sub>2</sub> grades scatter blue light more effectively than larger particle size grades and hence have a bluer undertone. The bluer undertone of R-706 imparts a brighter, cleaner tint.

### Shipping Containers

Ti-Pure™ R-706 is available in 25-kg paper bags and semi-bulk containers (1/2 and 1 metric ton). Truckload shipments of the dry product are available directly from Chemours. Less-than-truckload volumes are available through one of the authorized Chemours distributors.

Water slurries are available in some regions in truckload shipments (15 metric ton) and railcar (67 metric ton).

### Product Storage

The shelf life of Ti-Pure™ TiO<sub>2</sub> is indefinite as long as the material is kept from direct contact with moisture.

For further information about this grade or to request a sample, please see the Ti-Pure web site.

[www.titanium.chemours.com](http://www.titanium.chemours.com)

**CAUTION:** Do not use Chemours materials in medical applications involving permanent implantation in the human body or contact with bodily fluids or tissues, unless the material has been provided from Chemours under a written contract that is consistent with Chemours policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your Chemours representative. You may also visit [www.teflon.com/industrial](http://www.teflon.com/industrial) to download a copy of the "Chemours POLICY Regarding Medical Applications" C-00000 and "Chemours CAUTION Regarding Medical Applications" C-00000. For medical emergencies, spills, or other critical situations, call (800) 441-7515 within the United States. For those outside of the United States, call (302) 774-1000.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For more information, visit [www.titanium.chemours.com](http://www.titanium.chemours.com)

© 2015 The Chemours Company TT, LLC. Ti-Pure™ and any associated logos are trademarks or copyrights of The Chemours Company TT, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: H-56619-8  
C-10417 (7/15)