



# Ti-Pure™

## Select TS-6200 Titanium Dioxide

## Product Information

### Product Description

Ti-Pure™ Select TS-6200 is a rutile pigment manufactured via Chemour's chloride process. Designed specifically for the most demanding durability applications, Ti-Pure™ Select TS-6200 offers excellent gloss retention coupled with unique dispersing capabilities.

Ti-Pure™ Select TS-6200 is a fine dry powder with the following general properties:

**Table 1**

Analysis and Physical Properties of Ti-Pure™ Select TS-6200

Property	Value
TiO <sub>2</sub> , wt%	93
Alumina, wt%	3.6
Silica, wt%	3.3
Specific Gravity	4.0
Bulking Value, L/kg (gal/lb)	0.25 (0.03)
Organic Treatment	Yes
Color CIE L*	99.4
pH	8
Carbon Black Undertone	13.0

Note: All values are typical unless otherwise specified.

### Key Features

- High initial gloss
- Super durability
- Super processibility
- Excellent gloss retention
- All in one premium pigment

### Suggestions for Use

Ti-Pure™ Select TS-6200 is a specialty application pigment combining high gloss retention, good initial gloss, high hiding power, minimal dispersant demand and excellent dispersion. Recommended use is in:

- automotive coatings
- coil coatings
- durable industrial coatings
- fluorinated polymer coatings

### Excellent Gloss Retention

Gloss is an important feature in many super durable coatings applications, and retention of gloss over the life of a product is of high importance to consumers. Gloss retention is controlled by many factors, including resin chemistry and the inherent durability of the TiO<sub>2</sub> pigment employed in the coatings.

### Exceptional Durability via Silica Shell Technology

Ti-Pure™ Select TS-6200 couples an advanced silica coating technology with a proprietary surface treatment to give maximum resistance to photocatalytic degradation. This new technology represents a significant improvement over the traditional method of silica encapsulation found on most super durable TiO<sub>2</sub> pigments.

### Superior Chalk Resistance

Chalking and color fade are two common reasons for consumer dissatisfaction with durable coatings. Both are caused by the degradation of organic binder from the film surface, which leaves loosely attached TiO<sub>2</sub> particles on the coatings surface. This not only results in a "chalky" appearance to the coating, it also gives color fade because the exposed TiO<sub>2</sub> particles scatter light away from the film before it can interact with the colored pigments.

## Superior Dispersibility

The unique surface chemistry of Ti-Pure™ Select TS-6200 is tailor-made for easy dispersion—dispersion so easy that in some cases laborious, multi-step grinds can be reduced to a single, fast grind. Rapid dispersion results in greater rate, not only because dispersion times are decreased, but also because TiO<sub>2</sub> levels in the dispersion can be increased.

## Low Dispersant Demand

The improved dispersibility of Ti-Pure™ Select TS-6200 is also evident in its remarkably low dispersant demand. Ti-Pure™ Select TS-6200 needs as little as one fourth the dispersant load of other super durable pigments. Lower dispersant requirements can lead to significant cost savings, and by removing dispersant from the paint, the coatings manufacturer has the formulating flexibility to replace dispersant with other key ingredients.

**For safety information, please visit the product Safety Data Sheet (SDS).**

## Shipping Containers

Ti-Pure™ Select TS-6200 is available in 25-kg paper bags and 1 tonne semibulk containers. Truckload shipments of the dry product will be available directly from Chemours. Less-than-truckload volumes are available through authorized Ti-Pure distributors. Call your local sales office for the distributor nearest you.

## Product Storage

The shelf life of Ti-Pure™ Select TS-6200 is indefinite as long as the material is kept from direct contact with moisture.

For further information about this grade or to request a sample, please see the Ti-Pure™ web site.

[www.titanium.chemours.com](http://www.titanium.chemours.com)

**CAUTION:** Do not use Chemours materials in medical applications involving permanent implantation in the human body or contact with bodily fluids or tissues, unless the material has been provided from Chemours under a written contract that is consistent with Chemours policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your Chemours representative. You may also visit [www.teflon.com/industrial](http://www.teflon.com/industrial) to download a copy of the "Chemours POLICY Regarding Medical Applications" C-00000 and "Chemours CAUTION Regarding Medical Applications" C-00000. For medical emergencies, spills, or other critical situations, call (800) 441-7515 within the United States. For those outside of the United States, call (302) 774-1000.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

**For more information, visit [www.titanium.chemours.com](http://www.titanium.chemours.com)**

© 2015 The Chemours Company TT, LLC. Ti-Pure™ and any associated logos are trademarks or copyrights of The Chemours Company TT, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: K-07650  
C-10412 (7/15)