

# Ti-Pure<sup>®</sup> Select

## TS-6300 TITANIUM DIOXIDE

PRODUCT DATA SHEET

### Description

Ti-Pure<sup>®</sup> Select TS-6300 is a specialty TiO<sub>2</sub> designed for mid to high quality flat (matte) architectural coatings. It provides improved dry hiding power and quality consistency in a wide range of flat architectural coatings while maintaining film integrity. TS-6300 is a highly surface treated rutile titanium dioxide pigment manufactured by the chloride process, delivering exceptional brightness and maximum hiding power.

### Suggestions for Use

TS-6300 provides superior performance in flat (matte) architectural paints containing high levels of extenders and TiO<sub>2</sub> and formulated near or above the Critical Pigment Volume Concentration (CPVC). The TiO<sub>2</sub> particle size is optimized and the surface oxide treatment provides physical spacing in crowded systems, so that TiO<sub>2</sub> efficiency is maximized while maintaining the highest level of film integrity.

The weatherability performance of TS-6300 is adequate for many exterior architectural coatings but as this can be formula dependent, paint testing is highly recommended.

### Shipping Containers

Ti-Pure<sup>®</sup> Select TS-6300 is available in 25-kg paper bags and flexible intermediate bulk containers (0.65 and 0.5 metric ton). Truckload shipments may be available directly from DuPont.

### Product Storage

The shelf life of Ti-Pure<sup>®</sup> Select TiO<sub>2</sub> is indefinite as long as the material is kept in a dry location and not in direct contact with water or moisture.

### Typical Properties of TS-6300

Property	TS-6300
TiO <sub>2</sub> , wt%	min. 82
Specific Gravity	3.7
Bulking Value, L/kg (gal/lb)	0.27 (0.032)
Organic Treatment	No
Color CIE L*	100*
Median Particle Size**, μm	0.53
Oil Absorption	37*
pH	9*
Resistance at 30 °C (1 kohm)	6*
Carbon Black Undertone	10*

Note: All values are typical unless otherwise specified.

\*Properties listed on Certificate of Analysis

\*\*As measured by Horiba LA-300

Product safety information is available upon request.

The information set forth herein is furnished free of charge and based on technical data that DuPont believes to be reliable. It is intended for use by persons having technical skill, at their own risk. Since conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be taken as license to operate under or a recommendation to infringe any patents or trademarks.

Copyright © 2014 DuPont. All rights reserved. DuPont<sup>™</sup> and Ti-Pure<sup>®</sup> are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates.

K-15855 (09/14)